

PARQUET SEAL 12P

Revision:30/10/12**Product:**

PARQUET SEAL 12P is a high-quality, plasto-elastic one-component sealant based on acrylic dispersion

Technical Data:

Base	Acrylic Dispersion
Consistency	Pasta
Curing System	Physical Drying
Skin formation	Approx. 20 min. (20°C/65% R.H.)
Shrinkage	15% (DIN 52451)
Specific Gravity	1.65g/ML (DIN 53 479 B)
Temperature Resistance	-20°C to +80°C
Maximum allowed Distortion	15%

* This varies according to ambient conditions such as temperature, humidity, substrate etc.

**Characteristics:**

- Ready to use
- Solvent free
- Very easy to apply
- Colourfast and waterproof after curing
- Can be varnished after curing
- Very good adhesion on many porous surfaces

Applications:

- Filling of joints with movements up to 15%.
- Filling sealant for joints in parquet-, or laminate floors
- Connection joints between parquet floors, skirting board and walls
- Also suitable for cracks in wooden floors

Packaging:

Colour: pale oak, pale beech, oak, beech, merbau, maple, cherrywood

Packaging: cartridge 310mL

Shelflife:

At least 18 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°. Protect against frost!

Surfaces:

Type: all common wooden-, and laminate floors and porous building substrates.

State of Surface: clean, dry, free of dust and grease

We recommend a preliminary compatibility test.

Joint Size:

Minimum Width: 5mm

Maximum Width: 20mm

Minimum Depth: 5mm

Recommendation: depth = width

Applying the sealant:

Method: Handheld or pneumatic caulking gun.

Apply the sealant and smoothen with a filling-knife.

Apply a second layer of sealant in case of extreme shrinkage. Sandable after 24 hours.

Application temperature: +5°C to +30°C.

Clean: Uncured Parquet Seal 12P may be removed from parquet and tools with water. Cured sealant must be removed mechanically.

Repair: with the same material

Health- and safety recommendations:

Apply the usual industrial hygiene.

Consult the label for more information

Remarks:

- Do not use in applications where continuous water immersion is possible.
- PARQUET SEAL 12P can be varnished with most varnishes.
- The varnish should be sufficiently elastic to be applied on a plasto-elastic sealant. A preliminary test is recommended.

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.